



FC ME130BLUW



DESCRIPTION

Water slide decal for objects (**white or covering**)

TECHNICAL DATA

FC ME130BLUW is made of a 200 µm, 185 g/m² **light blue filter paper liner**, a **soluble polyvinyl layer** and a 24 µm **white composite polymer finish**.

EQUIPMENT

Color laser printer or copy machine + (possible) cutting plotter + water and rubber spatula

SUITABLE FOR

Various **colored materials**. Excellent for **glass**, **Plexiglas** and other **stiff materials** (eg. helmets or bottles). Also for **candles** or **découpage objects**. Ideal for **objects that resist to oven heating**.



FEATURES

FC ME130BLUW is a very thin **white** water slide decal, especially suitable for **flat or irregular** and **concave surfaces**. It **can be plotter cut**. It **sticks perfectly** on the object. Enhance **scratch resistance** with spray protectives or in some cases heat in oven.

INSTRUCTIONS

1



Insert the decal in the printer's by-pass and set to ultra-heavy **1 or 2 option (129-216 g/m²) mode**. Single sheet insertion. **Print in straight mode** on the light blue side.

2



Cutting option. If cutting is required prepare the file image with reference marks as indicated in the plotter's software. Cut the film as follows: use a blade for common or reflective vinyl with a 0,25 mm offset, 60 g pressure and 5-10 cm/s speed.
N.B. Cut only the film.

3



Dip the decal in a bowl of water for **1-2 minutes**. **Separate the film** from the paper liner by sliding it on the media with the printed side up. Weed away blank film if necessary.

N.B. Wet the substrate before proceeding with step 3

4



Whipe the decal with a rubber spatula (SPDECAL90) in center-outwards movements. Make sure all air and water bubbles are removed and that the film is perfectly attached to the object. Let dry for **6-8 hours**.

5



Improve scratch resistance by oven heating at 130°C-150°C for approximately **30 mins**. This step can be done only on heat-resistant objects.

WARNINGS

Decal decorated objects can be used only for ornamental reasons. For further details contact your dealer.

Store in a cool dry place.

Do not expose to direct sunlight.

If properly stored the product will maintain its features for at least 2 years.

STORAGE

The instructions on this sheet are merely indicative and contain details concerning tests carried out in our laboratories with our equipment. Do your own testing. The manufacturer will replace defective material but is not responsible for any damage resulting from incorrect use.

* Also available in 50 or 100/A4 packages

SHOCKLINE
about your transfer paper

T. +39 (0)875 751194 - F. +39 (0)875 751329
info@shockline.it - skype shock.line
www.shockline.it

code