



# FO PRIPELW



DESCRIPTION	White covering primer for FC FILM2 transfer paper	
TECHNICAL DATA	FO PRIPELW is made of a 120 µm, 115 g/m <sup>2</sup> <b>paper liner</b> , a 25 g/m <sup>2</sup> , 30 µm <b>polyethylenic layer</b> with a 10 µm <b>white polymeric finish</b> and a 8 g/m <sup>2</sup> <b>heat-melting polyurethane layer</b> .	
EQUIPMENT	Heat press or laminator	
SUITABLE FOR	Ideal in combination with FC FILM2 for customizing various colored materials; leather, leatherette, wood, cardboard, cork and canvas.	FEATURES
		FO PRIPELW is a <b>white primer</b> and in combination with FC FILM2 ensures <b>the personalization of dark or colored garments and accessories</b> .

INSTRUCTIONS		<b>1</b> After printing FC FILM2, <b>place</b> the glossy side of FO PRIPELW on the printed side of the transfer paper and <b>laminates</b> with a heat press or laminator.
		<b>2</b> <b>Laminator:</b> approx 130°C - speed 1
		<b>2</b> <b>Protect</b> the laminated papers <b>FC FILM2+FO PRIPELW</b> with a <b>soft silicone mat</b> (MA STUOI GB80-2). Then: <b>Air press:</b> 140°C for 40" - pressure 5atm <b>Manual press:</b> 140°C for 40" - high pressure <b>N.B.:</b> If no silicon pad is used, lower pressing times
		<b>3</b> Wait until it cools down and <b>remove the paper liner</b> from the <b>FO PRIPELW</b> . <b>Continue</b> as indicated on the FC FILM2 instructions (points 2 to 6).

WARNINGS	For materials with poor heat resistance press at approx. <b>100°C</b> . For further information contact your dealer.	STORAGE
		Store in a cool dry place. Do not expose to direct sunlight. If properly stored the product will maintain its features for at least 2 years.

The instructions on this sheet are merely indicative and contain details concerning tests carried out in our laboratories with our equipment. Do your own testing. The manufacturer will replace defective material but is not responsible for any damage resulting from incorrect use.  
\* Also available in 50/A4 and 100/A4 packages

**SHOCKLINE**  
about your transfer paper

T. +39 (0)875 751194 - F. +39 (0)875 751329  
info@shockline.it - skype shock.line  
www.shockline.it - www.digidecor.it

code